

3/7/1

DIALOG(R) File 351:Derwent WPI

(c) 2002 Derwent Info Ltd. All rts. reserv.

001994376

WPI Acc No: 1978-07389A/ 197804

**Bleaching pulp with hydrogen peroxide and Rongalite - used for treating  
e.g. chemical pulp and used paper**

Patent Assignee: AGENCY OF IND SCI & TECHNOLOGY (AGEN ); CHISSO ENG CO LTD  
(CHCC )

Number of Countries: 001 Number of Patents: 002

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 52148203	A	19771209				197804 B
JP 78029722	B	19780823				197837

Priority Applications (No Type Date): JP 7663889 A 19760601

Abstract (Basic): JP 52148203 A

Unbleached pulp is bleached with Rongalite after bleaching with H2O2. Other known bleaching process is pref. combined with this bleaching step. Unbleached or half-bleached pulp pretreated with hypochlorite pref. is used as the pulp material. Unbleached or half-bleached chemical pulp, half-chemical pulp such as SCP and CGP and regenerated pulp such as crashed pulp and used paper are effectively bleached. In an example 100 g of half-chemical pulp having 30 whiteness were bleached with H2O and Rongalite as follows. Pulp was sepd. with adding water and added 2% of H2O2 further added NaOH at pH 10-11 and maintained at 55 degrees C for 1 hr. To pulp treated with H2O2 was added 2% of Rongalite and maintained at 70 degrees C for 1 hr. to give pulp having 55 whiteness. The regenerated pulp and semi-bleached pulp were bleached in the similar process and to elevate 10-30 of whiteness.

Derwent Class: F09

International Patent Class (Additional): D21C-009/16